

ESTOVOSS SUPER

Description:

A 1 component PUR Coating, containing solvents which reacts to air humidity. Satin-shining paint for industrial floors and garages. Resistant to acids, soaks, oil and fuels. Suited for applications in- or outdoors, is UV resistant.

Application:

As watertightening of porous undergrounds. Finishing layer for concrete, metal indoors or outdoors. In case of fresh casted concrete, wait at least 28 days before applying G4 Primer and Estovoss. Easy to maintain. Finishing layer of a high quality for industrial purposes, balconies, agricultural industries, cellars or garages. Deliverable in 1-5-30kg packings.

Data by delivery:

Color :	grey
Viscosity :	
Gravity:	ca. 1,5 gr/cm ³
Tanableness :	6 months in closed coverage
Consistency :	liquid

Technical data:

Consumption :	300 gr/m ² /1st layer, 200 gr/m ² /2nd layer
Shore :	not appropriate

Processing:

Surface must be as dry and grease-proof as possible. Application of G4 Primer with brush or roll. After 2-4 hours (max. 12 hours) apply Estovoss with brush or roll. dust-dry after 2 hours. Wait between each layer for about 6-8 hours (max. 12 hours) Can be diluted with max. 10% PU-thinner. You can pass above after 6 hours, slightly assessable after 12 hours and completely cured after 7 days. To make the surface non-skid, you can use our non-skid granulat (5%). Stir well before use.

Safety:

Always wear protection clothings and gloves. Avoid contact with the skin. Cleanser for tools: Aceton or cleaner M, for hands: Slig
Attention: product is slightly flammable.